

# Zenith

GC1 karton

<b>Grammsúly/ Weight</b> ISO 536 g/m <sup>2</sup>	<b>215</b>	<b>235</b>	<b>250</b>	<b>270</b>	<b>295</b>	<b>325</b>	<b>350</b>	<b>380</b>
Vastagság/ Caliper ISO 534 µm	305	355	380	410	460	510	560	610
Merevség CD/ Stiffness CD ISO 2493 mNm	3.30 min	4.50 min	5.30 min	7.50 min	10.0 min	13.0 min	15.0 min	17.5 min
Merevség MD/ Stiffness MD ISO 2493 mNm	6.50 min	8.90 min	10.5 min	14.8 min	19.7 min	25.6 min	29.5 min	34.5 min
PPS ISO 8791-4 µm	1.70	1.70	1.70	1.70	1.70	1.70	1.70	1.70
Fényesség/ Brightness ISO 2470 %	91.5	91.5	91.5	91.5	91.5	91.5	91.5	91.5
Gloss 75 ISO 8254-1 %	45	45	45	45	45	45	45	45
Cobb 60s ISO 2471 %	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0
Ply bonding TAPPI 569 J/m <sup>2</sup>	130	130	130	130	130	130	130	130